

Description:

REPOIS P consists of a cement based external through coloured render. It is formed by a mortar base that is freshly applied by then dashing quartz aggregates, with a greater particle size than those found in the mortar.

Uses:

It is used for rendering facades made of blockwork or brickwork. It also gives uniformity to new jobs performed on concrete, brickwork, etc. It is also used for restoring purposes so as to replace paints and plastic renders.

Features & benefits:

WATERPROOFING.DECORATIVE.EXCELLENT ADHERENCE.

Surface preparation:

The background of application must be clean, resistant, uniform, free of grease, oil, and any ridges or irregularities.

Application:

- Mix with 26 %3% of water in weight using a concrete mixer or manually. Mix from 5 to 8 minutes.
- The open time of the mix is 45 to 60 minutes.
- Apply the fresh mortar using a trowel, projection machine by leaving at least 10 mm thick coating or an average thickness of 15 mm.
- Whilst the mortar mix is still fresh, proceed to limit the piers by placing the joint in the desired pattern: 7 m vertically and 2.5 m horizontally. The quartz aggregates are then dashed and pushed into the mortar, by floating if necessary so as to level both the aggregates and the mortar.

TechnicalFeatures:

Water absorption: $26 \pm 3\%$
Powder density: 1.230 ± 0.05 g/cc.
Mass of density: 1.750 ± 0.05 g/cc.
Curing density: 1.650 ± 0.05 g/cc.
Water retention: >97%
Capillarity: Adherence: > 2.5 kg/cm²
Compressive resistance: > 90 kg/cm²
Flexural strength resistance: > 35 kg/cm²

Coverage:

Pasta: 18 kg per m²; Grava: 10 to 12 kg per m².

Clean up:

Clean using large amounts of water.

Storage:

It is recommended to store this product for 1 year in tightly closed original packages.

The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.

Packaging:

Available in packs of:

P-A2, P-R.V., P-R.P, P-Z, P.R., P-V: 25 Kg

P-B, P-K2, P-C2, P-I, P-AK, P-S: 25 Kg

Health and safety advice :

R36/37/38 -- Irritating to eyes, respiratory system and skin

S2 -- Keep out of the reach of children

S8 -- Keep container dry

S24/25 -- Avoid any inhalation, contact with skin and eyes. Wear suitable protective clothing and gloves

S26 -- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice

S37/39 -- Wear suitable gloves and eye/face protection



The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.