

Technical Commercial data Sheet

Elastomat

Waterproofing bitumen polymer membrane



Dimensional features

Length	10 m - 1% 8 m - 1% (6 kg) (UNI EN 1848-1)	Toll. ≥
Width	1 m - 1% (UNI EN 1848-1)	Toll. ≥
Thickness	3; 4 mm (UNI EN 1849-1)	Toll. 0,4 mm
Weight per m ² (MINERAL)	4/4.5/5/5,5/6 kg (UNI EN 1849-1)	Toll. 10%

Description

The ELASTOMAT membranes are realized with a special compound based on bitumen modified with new generation elastomeric polymers (BPE), with -20°C cold flexibility. The reinforcement is in polyester reinforced with glass cloth.

The ELASTOMAT 4 MM P is also available in the "TEX" version with "DECOTEX" treatment, consisting in the application on the upper face of a special black polypropylenic tissue.

Application

- Use Personal Protective Equipment as requested by law;
- Clean properly the surface on which membranes has to be applied;
- ELASTOMAT is meant to be applied by flame with a gas propane blow torch by heating the lower face, covered with a special thermofusibile film;
- Apply between +5° C and + 35° C.

Recommended Use

The ELASTOMAT membranes are to be employed on several structure types. It is proper for base layers, basement structures, earth-retention walls and foundations. The MINERAL versions are meant to be used as finishing layer and/or as single layer.

Storage

It is advisable to keep the rolls in warehouse, not exposed to the sun rays and at a higher temperature than +5°C. Keep the rolls in the upright position. If possible, avoid stacking pallets, especially with slated membranes. It is advisable to use the product within 2/3 months from delivery.

TYPE	REINFORCEMENT	UPPER FACING	THICKNESS WEIGHT/m ²	m ² PER PALLET
ELASTOMAT 3 MM P	Polyester	Sand	3 mm	250
ELASTOMAT 4 MM P	Polyester	Sand	4 mm	230
ELASTOMAT TEX 4 MM P	Polyester	Polypropylene TNT	4 mm	230
ELASTOMAT MINERAL 4 KG P	Polyester	Slate	4 kg	250
ELASTOMAT MINERAL 4,5 KG P	Polyester	Slate	4,5 kg	230
ELASTOMAT MINERAL 5 KG P	Polyester	Slate	5 kg	230
ELASTOMAT MINERAL 5,5 KG P	Polyester	Slate	5,5 kg	200
ELASTOMAT MINERAL 6 KG P	Polyester	Slate	6 kg	184

Technical Commercial data Sheet

Elastomat

Technical features

Test	Standard Reference	ELASTOMAT P	ELASTOMAT MINERAL P	TOLERANCE
Visible Faults	UNI EN 1850-1	absent	absent	-
Straightness	UNI EN 1848-1	10 mm	10 mm	≤
Watertightness	UNI EN 1928	60 kPa	60 kPa	≥
Cold flexibility	UNI EN 1109	- 20 °C	- 20 °C	≤
Cold flexibility after ageing	UNI EN 1296 UNI EN 1109	- 15 °C	- 15 °C	+ 15 °C
L dimensional stability	UNI EN 1107-1	- 0,3 %	- 0,3 %	≥
Flow resistance	EN 1110	100 °C	100 °C	≥
Tensile strength at breaking L/T	UNI EN 12311-1	400 N/5 cm 300 N/5 cm	400 N/5 cm 300 N/5 cm	- 20 %
Elongation at breaking L/T	UNI EN 12311-1	35% 35%	35% 35%	- 15 a.v.
Tear resistance (B method) L/T	UNI EN 12310-1	130 N 130 N	130 N 130 N	- 30 %
Static load resistance	UNI EN 12730	10 Kg	10 Kg	≥
Dynamic punching resistance	UNI EN 12691	700 mm	700 mm	≥
Vapour permeability	UNI EN 1931	μ 20000	μ 20000	-
Fire reaction	EN 13501-1	NPD	NPD	-
External fire reaction	EN 13501-5	F roof	F roof	-
Granules adhesion	UNI EN 12039	-	30%	≤
Watertightness after exposure to chemical agents artificial ageing	UNI EN 1928 UNI EN 1847/ UNI EN 1296	NPD	-	-
Resistance to water penetration	UNI EN 1928	-	NPD	-
Resistance to water penetration Tensile properties	App. C EN 13859-1	-	NPD	-
Uses	EN 13707 System 2+	Base layer Middle layer	Top layer Single layer	-
	EN 13969 System 2+	Foundations Earth retention	-	-

The Saint-Gobain PPC Italia S.p.A. quality system is certified according to EN ISO 9001

Follow proper application and storage modalities.

The CE marking of this bituminous membrane is in accordance with the European Construction Products Regulation 305/2011, is in agreement to the reference technical standards and is supported by certification no. 1370-CPR-0050.

Saint Gobain PPC Italia has the right to change the technical data of this data sheet any time with no need of notice.

of notice.



Isover Saint-Gobain
è socio ordinario
del GBC Italia

CODICE: STCBE 005
REVISIONE: 07
DATA: april 2016
Pag. 2 di 2

