

Technical Commercial data Sheet

Bitumox

Oxyded bitumen cake



Recommended Use

BITUMOX is employed as glue for insulation panels or protection coating for concrete surfaces.

Description

Oxyded bitumen cakes for professional use in construction sites.

Packaging

30 kg bags.

Storage

Storage in covered, dry and aerated areas protected by U.V. rays is recommended.


Technical features	Bitumox
Composition	Mix of heavy aromatic, naphthenic, aliphatic hydrocarbons
Penetration at 25°C	10-20 dmm
Ring and ball point (PA)	90-100 °C
Ring and ball point (PA)	100-110 °C
Ductility at 25°C	> 3
Density at 25°C	1,01—1,06 kg/l
Flammability point	270 °C
Combustion point	280 °C
Heating loss at 200°C	< 0,2
Solubility in CS ₂	> 99,5
Sulphur content	< 6

Saint-Gobain Isover Italia S.p.A. quality system is certified according to EN ISO 9001.

The items of this technical data sheet are marketed by Saint Gobain PPC Italia. Consequently, the data here indicated have been obtained from the supplier's documents. The products are meant for proper modalities of application and storage and the technical data present in this document are indicative.

Saint Gobain PPC Italia has the right to carry out the changes or variations believed to be proper any time with no need of notice.

CODE: STCBE 029
REVISION: 02
DATE: DECEMBER 2012
PAGE: 1/1



Isover Saint-Gobain
è socio ordinario
del GBC Italia

Saint-Gobain PPC Italia S.p.A. – Attività Isover
Headquarters: Via Ettore Romagnoli, 6 – 20146 Milano
Customer Service Bituver: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. 0871/599022 - Fax 0871/ 552483
www.bituver.it

