

MINERAL FIBRE FABRIC FOR REINFORCING

white

Fiberglass mesh

Weight: 109 g/m2

Edition: 4 12/2010

#### Technical department

# **Description:**

TEJIAIS consists of a mineral fibre fabric used for reinforcing cement based or acrylic mortars. TEJIAIS is resistant to the alkaline characteristic of cement based materials.

Colour/s

Weight

Composition

#### Uses:

It is used as reinforcement in mortars, paints, cracks and fissures.

### Features & benefits:

DIMENSIONAL STABILITY.EXCELLENT MECHANICAL RESISTANCE.EXCELLENT CHEMICAL RESISTANCE.

#### Surface preparation:

Not applicable.

Clean up:

Not applicable.

### Application

Place in the centre of the product to be reinforced (plastic mortar, plaster, etc). The fabric is fixed into place using a serrated trowel, overlapping one fibre fabric with another until reaching 5 cm approximately. In cracks and fissures, it is recommended to establish double reinforcement, as well as in dintels and jambs.

### Packaging:

Available in packs of: TEJIAIS 1 : Roll 50 x 1 m de 58 gr/sqm

50 Squa TEJIAIS 10: Roll 50 x 1 m. 110 gr / sqm 50 Squa

TEJIAIS 5: Roll 50 x 1 m de 80 gr/sqm 50 Squa

TEJIAIS 5-160: Roll 50 x 1 m de 160 gr/sqm

50 Squa

#### Storage:

It is recommended to store this product in its original well packed rolls, protected from bleakness, with no exposure to extreme temperatures. No time limit for storage.

## Health and safety advice:

Consult the safety information on the label on each package, and for more information refer to the product Material Safety Data Sheet.

The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of it's useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.



PROFESSIONAL CONSTRUCTIVE SOLUTIONS ©TEAIS S.A. - All rights reserved - Avda. da Enerxía, nº 153, Pol. Ind. de Sabón - 15143 Arteixo, A Coruña Telf.: 981 602 111 - Fax: 981 601 508 - Email: comex@teais.es

# Coverage:

1.05 m2 per sqm.

**Technical features:**